K-FLEX[®] FOAM TAPE

Closed Cell Flexible Elastomeric Foam Insulation Thermal Performance for HVAC/R Applications



DESCRIPTION

K-FLEX[®] Foam Tape is an NBR/PVC-based closed cell, flexible elastomeric foam insulation tape with a factory-applied pressure sensitive adhesive that adheres firmly and forms a long-lasting bond. It is environmentally-friendly as it is free of CFCs, HFCs, HCFCs, PBDEs, formaldehyde and fibers. An EPA-registered antimicrobial agent is incorporated into the product providing additional protection against mold, fungal and bacterial growth. The product is made in K-FLEX USA's ISO 9001:2008-certified manufacturing facility in North Carolina.

AVAILABILITY

K-FLEX[®] Foam Tape is black in color and is available in 1/8" or 1/4" thick by 2" wide by 30' long rolls.

APPLICATIONS

K-FLEX[®] Foam Tape is recommended for applications with service temperatures ranging from -40°F (-40°C) to +200°F (+93°C). The product is used to retard heat gain/loss on belowambient to medium hot applications. It is ideal for insulating short runs of pipes or valves and fittings where it is impractical to install tubing insulation. The tape can be applied in multiple layers to meet various service conditions. It is not recommended for use with heat trace tapes for freeze protection applications.

OUTDOOR APPLICATIONS

K-FLEX[®] Foam Tape is recommended for indoor use only to protect it from external environment conditions.

INSTALLATION

K-FLEX® Foam Tape is flexible (even at low temperatures), durable (non-fracturing and resistant to tearing from handling and environment), safe to handle (non-dusting and non-abrasive), and lightweight for an efficient installation. K-FLEX recommends that insulation is installed on non-operational systems with clean, dry surfaces in ambient conditions between 40°F and 100°F. K-FLEX® Foam Tape can be applied to any diameter pipe by spiral winding with 50% overlap per layer until the desired thickness is obtained (removing the release paper as the tape is wrapped). Stretching should be avoided, edges may be butted or overlapped, and seams should be sealed with proper pressure, which is critical as the PSA backing is application

temperature sensitive.

RESISTANCE TO MOISTURE VAPOR FLOW

The expanded closed cell structure and unique formulation inherently resists moisture vapor intrusion and is considered a Class 1 vapor retarder per ASHRAE. For most indoor applications, K-FLEX[®] Foam Tape needs no additional protection. Additional vapor barrier protection may be necessary when installed on cold surfaces that are exposed to continuous high humidity.

FLAME AND SMOKE RATING

K-FLEX[®] Foam Tape has a flame spread rating of 25 or less and a smoke development rating of 50 or less as tested to ASTM E84, "Surface Burning Characteristics of Building Materials". It is acceptable for duct/plenum applications, meeting the requirements of NFPA 90A/B.

Numerical flammability ratings alone may not define the performance of products under actual fire conditions. They are provided only for use in the selection of products to meet limits specified when compared to a known standard.

PHYSICAL PROPERTIES		K-FLEX® FOAM TAPE	TEST METHODS
Main Composition		Flame-retarded NBR/PVC-based elastomeric foam with a solvent-free, acrylic dispersion high tack	
		adhesive with good resistance to moisture and aging	
Thermal Conductivity (Btu-in/hr-Ft²-°F)	75°F (24°C) Mean Temp	0.245	ASTM C177
Density		3-5 lb/ft ³	ASTM D1667
Operating Temperature Range		-40°F (-40°C) to +200°F (+93°C)	ASTM C534
Water Vapor Permeability (Dry Cup)		<0.01 perm-in	ASTM E96
Water Absorption (Volume Change)		0%	ASTM C209
Flame Spread / Smoke Development (up to 2")		<25/50	ASTM E84
Flexibility		Pass: Cold Crack Test at -40°F (-40°C)	ASTM D1056
Freight Classification		Tape, insulation, NOIBN. No label required.	
Adhesive Thickness		0.07 mm	
Adhesive Peel Resistance		≥20 N / 25 mm	DIN EN 1939
Adhesive Shear Adhesion		500 g/625 mm ²	DIN EN 1943

THICKNESS RECOMMENDATIONS (LAYERS OF 1/8" TAPE)				
Ambient Conditions	50°F (10°C) Process Temperature	32°F (0°C) Process Temperature		
77°F (25°C) / 50% RH	1 Layer	2 Layers		
85°F (29°C) / 70% RH	3 Layers	4 Layers		



METRO SUPPLY COMPANY

12 Andrews Drive Woodland Park, NJ 07424 Telephone: 973-237-1551 fax: 973-237-1552 Internet: www.metrosupplycompany.com Email: info@metro-supply-co.com