

Technical Product Information

BOARD INSULATION 15080* PROCESS EQUIPMENT INSULATION 40 42 23** MINERAL BOARD INSULATION 07 21 13**

General Product Information: Description & Common Applications:

ROXUL® products are mineral wool fibre insulations made from basalt rock and slag. This combination results in a noncombustible product with a melting point of approximately 2150°F (1177°C), which gives it excellent fire resistance properties. ROXUL mineral wool is a water repellent yet vapour permeable material.

The RHT® 120 product is a non-combustible, rigid mineral wool insulation board that is water repellent and designed for high temperature applications where durability and compressive resistance are required. Common application areas for the RHT series of board insulation include storage tank insulations, drying/oven equipment, petro-chemical and power generating equipment protection where high temperature, fire resistance, and moisture resistance are concerns.

Compliance and Performance:

ASTM C 612 Mineral Fiber Block and Board Thermal Insulation Type IVB, Complies

MEA Approval 334-97-M New York City Approval City Of Los Angeles Approval RR 25444

Fire Performance:

ASTM F 136 Behaviour of Materials at 750°C (1382°F) Non-Combustible

CAN4 S114 Test for Non-Combustibility Non-Combustible **ASTM E 84(UL 723)** Surface Burning Characteristics Flame Spread = 0 Smoke Developed = 0CAN/ULC S102 Surface Burning Characteristics Flame Spread = 0

Smoke Developed = 0

Maximum Service Temperature:

Hot Surface Performance ASTM C 411 In Compliance with

ASTM C612 @ 1200°F(650°C)

Dimensional Stability:

ASTM C 356 <1% @ 1200°F (650°C) Linear Shrinkage

Moisture Resistance:

ASTM C 1104 Moisture Sorption 0.01%

Thermal Resistance:

ASTM C 518 (C 177) R-value/inch @ 75°F 4.0 hr.ft2,F/Btu***

RSI value/25.4 mm @ 24°C 0.71 m²K/W

Corrosive Resistance:

ASTM C 665 Corrosiveness to Steel


ASTM C 795 **** Stainless Steel Stress Corrosion Specification as per Test


Methods C871 and C692: U.S. Nuclear Regulatory Commission, Reg. Guide #1.36: U.S. Military Specifications MIL-I-24244 (all

versions including B and C)



Thermal Conductivity:





Compressive Strength:

ASTM C 165 at 10%: 418 psf (20 kPa) at 25%: 877 psf (42 kPa)

Density:

ASTM C 612-93 - Nominal 12.0 lbs/ft³ 192 kg/m³

ASTM C 612-00 - Actual

8.6 lbs/ft³ 137 kg/m³

Dimensions:

24" (width) x 48" (length) 610 mm (width) x 1219 mm (length)

Thickness:

Product thickness is available in 1" through 4" in 1/2" increments

For additional sizes, please contact our customer service representatives.

Facing:

This product can be faced with reinforced foil. Please note that the facing will influence the product's service temperature range.



Key Application Qualifiers:

- Easy to install
- Service temperature 1200°F (650°C)
- Non-combustible
- · Can be fabricated/laminated
- · Low moisture sorption
- · Good compressive resistance
- Non-corrosive
- · Chemically inert
- CFC and HCFC free product and process
- · Made from natural & recycled materials

Other ROXUL Products:

Please consult ROXUL for all your insulation needs. We have an extensive range of products for all applications from pipe insulation to commercial products to residential batts. ROXUL invites all inquiries and will act promptly to service all of your requirements.

**** "Provisions for lot testing may be required, consult manufacturer."

Note:

As ROXUL Inc. has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's. products. ROXUL Inc's. overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

ROXUL INC.
www.roxul.com

Milton, Ontario Tel: 905-878-8474 Tel: 1-800-265-6878

Fax: 1-800-991-0110 Revised: August 7, 2007 Supersedes: June 1, 2007

Fax: 905-878-8077